

Rhenocoll PUR Siegel High Solid, wood lacquer, colorless

Rhenocoll solvent-**Klassik** Industrial product

Art. no.: A 4141

Specifications: Two-component lacquer based on polyurethane, ready for use after mixing with hardener, fast-drying and PVC-steady. Excellent resistance against chemical and mechanical stress. Very good filling properties. High-quality refining of wooden surfaces such as seating furniture, tables, furniture for laboratories and schools, shop fittings. Resistant against many factors such as water, dirt, grease, oil and different solvents, also acetone, ink, thinned acids and alkalis.

Application: by brush, spraying device or by pouring.

Must be mixed with PUR-Hardener 4003 or PUR-Hardener 4005

Mixing ratio:

PUR-Hardener 4003 1:10 PUR-Siegel High Solid

PUR-Hardener 4005 1:2 PUR-Siegel High Solid

For professional use.

Features: Preservative free

Delivery form/Color: transparent, colorless

Degree of gloss:

Standard: no.: 4114 = satin matt

Special adjustments: no.: 4110 = glossy

no.: 4112 = satin gloss

no.: 4117 = matt

Substrate: Any hard- and softwood. Veneer and board material made of wood, chipboard, MDF.

Further treatment: PUR-Siegel can be used as a primer and as a final coat.

Consumption: 150 ml/m² (per application)

VOC 2010: n/a

Labeling:

GefStoffV: UN 1263 paint, 3, II, ADR

Safety advice:

F Highly flammable

Xn Harmful

contains Toluene

R-phrases:

11 Highly flammable

20/21 Harmful by inhalation and in contact with skin.

36 Irritant to eyes.

- 48/20 Harmful: danger of serious damage to health by prolonged exposure through inhalation.
63 Possible risk of harm to the unborn child.

S-phrases:

- 53 Avoid exposure – obtain special instructions before use.
13 Keep away from food, drink and animal feeding stuffs.
16 Keep away from sources of ignition – no smoking.
26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
33 Take precautionary measures against static discharge.
36/37 Wear suitable protective clothing and gloves.
51 Use only in well ventilated areas.

Storage:

Keep container firmly closed and store cool and at a well-ventilated area. Open and handle with precaution. Protect from heat and direct sunlight. Do not store at temperatures below 5°C and above 30°C.

Supply units:

<i>PUR-Siegel High Solid</i>	<i>PUR-Härter 4003</i>	<i>PUR-Härter 4005</i>
5 ltr. canister	500 ml bottle	2.5 ltr. canister
30 ltr. canister	3 ltr. canister	5 ltr. canister
200 ltr. barrel	30 ltr. hobbock	30 ltr, hobbock 200 ltr. barrel

Disposal:

Not fully hardened or dried product residue is to be disposed of as special waste (AVV waste key no. 08 01 11). Empty packaging is to be recycled.

Ecology:

Water hazard class: WGK 2

Service:

Our service team for application technology is available to you at any time without obligation.

Phone: ++49 (0)6384 99 38 - 0
Fax: ++49 (0)6384 99 38 - 112
Email: info@rhenocoll.de

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case.

With the release of this Technical Data Sheet all previous versions become obsolete.